





## **European Technical Assessment**

ETA 17/0005 of 10/09/2019

Technical Assessment Body issuing the ETA: Technical and Test Institute

for Construction Prague

Trade name of the construction product Injection system Hilti HIT-1 / HIT-1 CE

Product family to which the construction

product belongs

eota@tzus.cz

Bonded injection type anchor for use in

non-cracked concrete

Product area code: 33

Manufacturer Hilti AG

Feldkircherstraße 100

9494 Schaan

FÜRSTENTUM LIECHTENSTEIN

Manufacturing plant(s) Hilti Werke

**This European Technical Assessment** 

contains

15 pages including 12 Annexes which form

an integral part of this assessment.

This European Technical Assessment is issued in accordance with regulation (EU) No 305/2011, on the basis of

This version replaces

EAD 330499-01-0601

ETA 17/0005 issued on 23/07/2019

Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full (excepted the confidential Annex(es) referred to above). However, partial reproduction may be made, with the written consent of the issuing Technical Assessment Body - Technical and Test Institute for Construction Prague. Any partial reproduction has to be identified as such.

#### 1. Technical description of the product

The Injection system Hilti HIT-1 / HIT-1 CE polyester resin styrene-free for non-cracked concrete is a bonded anchor consisting of a cartridge with injection mortar and a steel element. The steel elements consists of a commercial threaded rods, a hexagon nut and a washer. The steel elements are made of galvanized steel or stainless steel.

The steel element is placed into a drilled hole filled with injection mortar and is anchored via the bond between metal part, injection mortar and concrete.

The illustration and the description of the product are given in Annex A.

#### 2. Specification of the intended use in accordance with the applicable EAD

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The provisions made in this European Technical Assessment are based on an assumed working life of the anchor of 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the products in relation to the expected economically reasonable working life of the works.

## 3. Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance to tension load	Annex C 1
(static and quasi-static loading)	Affilex C 1
Characteristic resistance to shear load	Annex C 2
(static and quasi-static loading)	Affilex C 2
Displacements under short term and long term loading	Annex C 3
Durability	Annex B 1

#### 3.2 Hygiene, health and environment (BWR 3)

No performance determined.

#### 3.3 General aspects relating to fitness for use

Durability and serviceability are only ensured if the specifications of intended use according to Annex B1 are kept.

## 4. Assessment and verification of constancy of performance (AVCP) system applied with reference to its legal base

According to the Decision 96/582/EC of the European Commission<sup>1</sup> the system of assessment verification of constancy of performance (see Annex V to Regulation (EU) No 305/2011) given in the following table applies.

 Product
 Intended use
 Level or class
 System

 Metal anchors for use in concrete
 For fixing and/or supporting to concrete, structural elements (which contributes to the stability of the construction works) or heavy units
 1

Official Journal of the European Communities L 254 of 08.10.1996

## 5. Technical details necessary for the implementation of the AVCP system, as provided in the applicable EAD

#### 5.1 Tasks of the manufacturer

The manufacturer may only use raw materials stated in the technical documentation of this European Technical Assessment.

The factory production control shall be in accordance with the control plan which is a part of the technical documentation of this European Technical Assessment. The control plan is laid down in the context of the factory production control system operated by the manufacturer and deposited at Technický a zkušební ústav stavební Praha, s.p.<sup>2</sup> The results of factory production control shall be recorded and evaluated in accordance with the provisions of the control plan.

#### 5.2 Tasks of the notified bodies

The notified body shall retain the essential points of its actions referred to above and state the results obtained and conclusions drawn in a written report.

The notified certification body involved by the manufacturer shall issue an certificate of constancy of performance of the product stating the conformity with the provisions of this European Technical assessment.

In cases where the provisions of the European Technical Assessment and its control plan are no longer fulfilled the notified body shall withdraw the certificate of constancy of performance and inform Technický a zkušební ústav stavební Praha, s.p without delay.

Issued in Prague on 10.09.2019

Ву

Ing. Mária Schaan Head of the Technical Assessment Body

The control plan is a confidential part of the documentation of the European Technical Assessment, but not published together with the ETA and only handed over to the approved body involved in the procedure of AVCP.

# **Installed condition** Figure A1: Threaded rod, HAS-U-..., HIT-V-... Marking of the embedment depth $h_0 = h_{ef}$ $\mathsf{t}_{\mathsf{fix}}$ Injection system Hilti HIT-1 / HIT-1 CE Annex A 1 **Product description** Installed conditions




Table A1: Ma	aterials
--------------	----------

Designation	Material			
Metal parts made of	zinc coated steel			
HAS-U-5.8 (HDG), HIT-V-5.8(F), Threaded rod	Strength class 5.8, $f_{uk}$ = 500 N/mm², $f_{yk}$ = 400 N/mm² Elongation at fracture ( $I_0$ = 5d) > 8% ductile Electroplated zinc coated $\geq$ 5 $\mu$ m, (F) or (HDG) hot dip galvanized $\geq$ 45 $\mu$ m			
HAS-U-8.8 (HDG), HIT-V-8.8(F), Threaded rod	Strength class 8.8, $f_{uk}$ = 800 N/mm², $f_{yk}$ = 640 N/mm² Elongation at fracture ( $I_0$ = 5d) > 12% ductile Electroplated zinc coated $\geq$ 5 $\mu$ m, (F) or (HDG) hot dip galvanized $\geq$ 45 $\mu$ m			
Washer	Electroplated zinc coated ≥ 5 μm, hot dip galvanized ≥ 45 μm			
Nut	Strength class of nut adapted to strength class of threaded rod Electroplated zinc coated $\geq$ 5 $\mu$ m, hot dip galvanized $\geq$ 45 $\mu$ m			
Metal parts made of	stainless steel			
HAS-U A4, HIT-V-R	strength class 70, fuk = 700 N/mm <sup>2</sup> , fyk = 450 N/mm <sup>2</sup> Elongation at fracture ( $l_0 = 5d$ ) > 8% ductile Stainless steel A4 according to EN 10088-1:2014			
Threaded rod,	strength class 70, fuk = 700 N/mm², fyk = 450 N/mm² Elongation at fracture ( $l_0$ = 5d) > 8% ductile Stainless steel 1.4401, 1.4404, 1.4578, 1.4571, 1.4439, 1.4362 EN 10088-1:2014			
Washer	Stainless steel A4 according to EN 10088-1:2014			
Nut	Strength class of nut adapted to strength class of threaded rod Stainless steel A4 according to EN 10088-1:2014			
Metal parts made of	high corrosion resistant steel			
HAS-U HCR, HIT-V-HCR	fuk = 800 N/mm <sup>2</sup> , fyk = 640 N/mm <sup>2</sup> Elongation at fracture ( $l_0$ = 5d) > 8% ductile High corrosion resistant steel according to EN 10088-1:2014			
Threaded rod	fuk = 800 N/mm <sup>2</sup> , fyk = 640 N/mm <sup>2</sup> Elongation at fracture ( $l_0$ = 5d) > 8% ductile High corrosion resistant steel 1.4529, 1.4565 EN 10088-1:2014			
Washer	High corrosion resistant steel according to EN 10088-1:2014			
Nut	Strength class of nut adapted to strength class of threaded rod High corrosion resistant steel according to EN 10088-1:2014			

Injection system Hilti HIT-1 / HIT-1 CE	
Product description Materials	Annex A 3

#### Specifications of intended use

#### Anchorages subject to:

Static and quasi static loading.

#### Base material:

- Reinforced or unreinforced normal weight concrete according to EN 206-1:2013.
- Strength classes C20/25 to C50/60 according to EN 206-1:2013.
- Uncracked concrete

#### Temperature in the base material:

- · at installation
  - 5 °C to +40 °C
- · in-service

Temperature range I: - 40 °C to +40 °C

(max long term temperature +24 °C and max short term temperature +40 °C)

Temperature range II: - 40 °C to +80 °C

(max long term temperature +50 °C and max short term temperature +80 °C)

Table B1: Specifications of intended use

TT Opcomoducino		·
		HIT-1 / HIT-1 CE with
Elements		Threaded rod, HAS-U, HIT-V
Hammer drilling		✓
Use category  Dry or wet concrete (not in flooded holes)		✓
Static and quasi static loading in uncracked concrete		M8 to M16

#### **Use conditions (Environmental conditions):**

- Structures subject to dry internal conditions (zinc coated steel, stainless steel or high corrosion resistant steel).
- Structures subject to external atmospheric exposure (including industrial and marine environment) and to permanently damp internal conditions, if no particular aggressive conditions exist (stainless steel or high corrosion resistant steel).
- Structures subject to external atmospheric exposure and to permanently damp internal conditions, if other particular aggressive conditions exist (high corrosion resistant steel).

Note: Particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor swimming pools or atmosphere with extreme chemical pollution (e.g. in desulphurization plants or road tunnels where de-icing materials are used).

Injection system Hilti HIT-1 / HIT-1 CE	
Intended use Specifications	Annex B 1

#### Design:

- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored. The
  position of the anchor is indicated on the design drawings (e. g. position of the anchor relative to
  reinforcement or to supports, etc.).
- The anchorages are designed in accordance with: EN 1992-4:2018

#### Installation:

- Use category: dry or wet concrete (not in flooded holes)
- Drilling techniqué:
  - Hammer drilling
- Installation direction D3: downward and horizontal and upward (e.g. overhead) installation admissible for all elements.
- Anchor installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site

Injection system Hilti HIT-1 / HIT-1 CE	
Intended use Specifications	Annex B 2

Table B2: Installation parameters for threaded rod, HAS-U-..., HIT-V-...

Threaded rod, HAS-U, HIT-V			M 8	M 10	M 12	M 16
Diameter of element	d	[mm]	8	10	12	16
Nominal diameter of drill bit	$d_0$	[mm]	10	12	14	18
Effective embedment depth a drill hole depth	$h_{\text{ef}} = h_0$	[mm]	60 to 160	60 to 200	70 to 240	80 to 320
Maximum diameter of clearance hole in the fixture	d <sub>f</sub>	[mm]	9	12	14	18
Diameter of steel brush	$d_b$	[mm]	10	12	14	18
Minimum thickness of member	h <sub>min</sub>	[mm]	h <sub>ef</sub> + 30 mm ≥ 100 mm			h <sub>ef</sub> + 2d <sub>0</sub>
Maximum torque moment	$T_{max}$	[Nm]	10	20	40	80
Minimum spacing	S <sub>min</sub>	[mm]	40	50	60	80
Minimum edge distance	Cmin	[mm]	40	50	60	80



#### Marking:

Steel grade number and length identification letter: e.g. 8L



#### Marking:

5.8 - I = HIT-V-5.8 M...x I 5.8F - I = HIT-V-5.8F M...x I 8.8 - I = HIT-V-8.8 M...x I 8.8F - I = HIT-V-8.8F M...x I R - I = HIT-V-R M...x I HCR - I = HIT-V-HCR M...x I

#### Injection system Hilti HIT-1 / HIT-1 CE

Intended use

Installation parameters of threaded rod, HAS-U-..., HIT-V-...

Annex B 3

Table B3: Maximum working time and minimum curing time 1)

Temperature in the b	ase material	Maximum working time twork	Minimum curing time t <sub>cure</sub>
-5 °C to -	1 °C	1,5 hours	6 hours
0°C to +	⊦4 °C	45 min	3 hours
+5 °C to +	⊦9 °C	25 min	2 hours
+10 °C to +	⊦14 °C	20 min	100 min
+15 °C to +	⊦19 °C	15 min	80 min
+20 °C to +	+29 °C	6 min	45 min
+30 °C to +	+34 °C	4 min	25 min
+35 °C to +	+39 °C	2 min	20 min

<sup>1)</sup> The curing time data are valid for dry base material only. In wet base material the curing times must be doubled.

Table B4: Parameters of cleaning and setting tools

Elements	Drill and	Installation	
Threaded Rod, HAS-U, HIT-V	Hammer drilling	Brush	Piston plug
size	d₀ [mm] HIT-RB		HIT-SZ
M8	10	10	10
M10	M10 12		12
M12	M12 14 14		14
M16	M16 18 18		18

#### Cleaning alternatives

## Manual Cleaning with Machine Brushing (MCMB):

Hilti hand pump for blowing out drill holes with diameters  $d_0 \le 20$  mm and drill hole depths  $h_0 \le 10 \cdot d$ 



## Compressed Air Cleaning with Machine Brushing (CACMB):

Air nozzle with an orifice opening of minimum 3,5 mm in diameter (min. 6 bar).




Injection system Hilti HIT-1 / HIT-1 CE	
Intended use	Annex B 4
Maximum working time and minimum curing time	
Parameters of cleaning and setting tools	

#### Installation instruction

#### Hole drilling

#### Hammer drilling




Drill with hammer drill a hole into the base material to the size and embedment depth required by the selected anchor (Table B2). In case of aborted drill hole: the drill hole shall be filled with mortar.

#### **Drill hole cleaning**

Just before setting an anchor, the drill hole must be free of dust and debris. Inadequate hole cleaning = poor load values.


### Manual Cleaning with Machine Brushing (MCMB)

for drill hole diameters  $d_0 \le 20$  mm and drill hole depths  $h_0 \le 10 \cdot d$ 




The Hilti hand pump may be used for blowing out drill holes up to diameters  $d_0 \le 20$  mm and embedment depths up to  $h_{ef} \le 10 \cdot d$ .

Blow out at least 4 times from the back of the drill hole until return air stream is free of noticeable dust.



Check brush diameter (Table B2) and attach the brush to a drilling machine or a battery screwdriver. Brush the hole with an appropriate sized HIT-RB wire brush (Table B4) a minimum of four times.


The brush must produce natural resistance as it enters the drill hole (brush  $\emptyset \ge$  drill hole  $\emptyset$ ) - if not the brush is too small and must be replaced with the proper brush diameter.



Blow out again with the Hilti hand pump at least 4 times until return air stream is free of noticeable dust.


## Compressed Air Cleaning with Machine Brushing (CACMB)

for all drill hole diameters do and all drill hole depths ho




Blow 4 times from the back of the hole (if needed with nozzle extension) over the hole length with oil-free compressed air (min. 6 bar at 6 m³/h) until return air stream is free of noticeable dust.

For drill hole diameters  $\geq$  32 mm the compressor has to supply a minimum air flow of 140 m<sup>3</sup>/h.



Check brush diameter (Table B2) and attach the brush to a drilling machine or a battery screwdriver. Brush the hole with an appropriate sized HIT-RB wire brush (Table B4) a minimum of four times.

The brush must produce natural resistance as it enters the drill hole (brush  $\emptyset \ge$  drill hole  $\emptyset$ ) - if not the brush is too small and must be replaced with the proper brush diameter.




Blow again with compressed air 4 times until return air stream is free of noticeable dust.

#### Injection system Hilti HIT-1 / HIT-1 CE

Intended use Installation instructions Annex B 5


#### Injection preparation



Tightly attach new Hilti mixing nozzle HIT PM to foil pack manifold (snug fit). Do not modify the mixing nozzle.


Observe the instruction for use of the dispenser.

Check foil pack holder for proper function. Do not use damaged foil packs / holders. Insert foil pack into foil pack holder and put holder into HIT-dispenser.




Prior to dispensing into the drill hole, squeeze out separately a minimum of three full strokes and discard non-uniformly mixed adhesive components until the mortar shows a consistent grey colour. For foil tube cartridges it must be discarded a minimum of six full strokes.

**Inject adhesive** from the back of the drill hole without forming air voids.




Inject the adhesive starting at the back of the hole, slowly withdrawing the mixer with each trigger pull.

Fill approximately 2/3 of the drill hole to ensure that the annular gap between the anchor and the concrete is completely filled with adhesive along the embedment length.




After injection is completed, depressurize the dispenser by pressing the release trigger. This will prevent further adhesive discharge from the mixer.




Overhead installation and/or installation with embedment depth hef > 250mm. For overhead installation the injection is only possible with the aid of extensions and piston plugs. Assemble HIT PM mixer, extension(s) and appropriately sized piston plug (see Table B4). Insert piston plug to back of the hole and inject adhesive. During injection the piston plug will be naturally extruded out of the drill hole by the adhesive pressure.


#### Setting the element



Before use, verify that the element is dry and free of oil and other contaminants. Mark and set element to the required embedment depth until working time twork has elapsed. The working time twork is given in Table B3.



For overhead installation use piston plugs and fix embedded parts with e.g. wedges.



Loading the anchor: After required curing time t<sub>cure</sub> (see Table B3) the anchor can be loaded

The applied installation torque shall not exceed the values  $T_{max}$  given in Table B2.

#### Injection system Hilti HIT-1 / HIT-1 CE

Intended use

Installation instructions

Annex B 6

Table C1: Essential characteristics for threaded rod, HAS-U-..., HIT-V-... under tension load in uncracked concrete

Threaded rod, HAS-U, HIT-V			M 8	M 10	M 12	M 16		
Installation safety factor	γinst [-]			1,2				
Steel failure		·						
Characteristic resistance	N <sub>Rk,s</sub>	[kN]	$A_s \cdot f_{uk}$					
Partial factor grade 5.8	γMs,N <sup>1)</sup>	[-] 1,5						
Partial factor grade 8.8	γMs,N <sup>1)</sup>	[-]			1,5			
Partial factor HAS-U A4, HIT-V-R	$\gamma_{Ms,N}$ 1)	[-]			1,86			
Partial factor HAS-U HCR, HIT-V-HCR	$\gamma_{Ms,N}$ 1)	[-]			1,5			
Combined pullout and concrete cone	failure							
Characteristic bond resistance in uncra	cked concr	ete C20/25						
Temperature range I: 40°C/24°C	$ au_{Rk,ucr}$	[N/mm²]	7,0	7,0	7,0	6,0		
Temperature range II: 80°C/50°C	$ au_{Rk,ucr}$	[N/mm²]	5,0	5,0	5,0	4,5		
Influence factors ψ on bond resistan	ce τ <sub>Rk</sub>	-	'			•		
		C25/30	1,04					
		C30/37	1,08					
Uncracked concrete:		C35/45	1,13					
Factor for concrete strength	Ψc C40/50		1,15					
		C45/55	1,17					
		C50/60	1,19					
Concrete cone failure								
Factor for uncracked concrete	$k_{\text{ucr},N}$	[-]			11,0			
Edge distance	Ccr,N	[mm]		1	,5 ⋅ h <sub>ef</sub>			
Spacing	Scr,N	[mm]	3,0 · h <sub>ef</sub>					
Splitting failure					- b /b - 3			
	h / hef ≥ 2,0		1,0 · hef					
Edge distance c <sub>cr,sp</sub> [mm] for	2,0 > h / hef > 1,3		4,6 hef - 1,8 h					
	h / hef ≤ 1,3		2,26 hef			1,0·h <sub>ef</sub> 2,26·l		
Spacing	S <sub>cr,sp</sub>	[mm]		2	2 Ccr,sp	,ei,		

Injection system Hilti HIT-1 / HIT-1 CE	
Performances	Annex C 1
Essential characteristics under tension load in concrete	

Table C2: Essential characteristics for threaded rod, HAS-U-..., HIT-V-... under shear load in uncracked concrete

Threaded rod, HAS-U, HIT-V			M 8	M 10	M 12	M 16
Steel failure without lever arm						
Characteristic shear resistance	$V_{Rk,s}$	[kN]	0,5 · A <sub>s</sub> · f <sub>uk</sub>			
Partial factor grade 5.8	γMs,V <sup>1)</sup>	[-]	1,25			
Partial factor grade 8.8	γMs,V <sup>1)</sup>	[-]	1,25			
Partial factor HAS-U A4, HIT-V-R	γMs,V <sup>1)</sup>	[-]	1,56			
Partial factor HAS-U HCR, HIT-V-HCR	γMs,V <sup>1)</sup>	[-]	1,25			
Ductility factor	k <sub>7</sub>	[-]	1,0			
Steel failure with lever arm		·				
Characteristic bending moment	M <sup>0</sup> Rk,s	[Nm]	1.2 · W <sub>el</sub> · f <sub>uk</sub>			
Ductility factor	k <sub>7</sub>	[-]	1,0			
Concrete pry-out failure		·				
Pry-out factor	k <sub>8</sub>	[-]	2,0			
Concrete edge failure						
Effective length of fastener	lf	[-]	min (h <sub>ef</sub> ; 12·d <sub>nom</sub> )			
Outside diameter of fastener	d <sub>nom</sub>	[-]	8 10 12 16			16

<sup>&</sup>lt;sup>1)</sup> In absence of national regulations.

Injection system Hilti HIT-1 / HIT-1 CE	
Performances Essential characteristics under shear load in concrete	Annex C 2

#### Table C3: Displacements under tension load

Threaded rod, HAS-U, HIT	-V		M 8	M 10	M 12	M 16
Uncracked concrete temperatu	40°C/24°C					
Displacement	δ <sub>N0</sub> -factor	[mm/(N/mm²)]	0,03	0,04	0,05	0,07
	δ <sub>N∞</sub> -factor	[mm/(N/mm²)]	0,07	0,08	0,08	0,08
Uncracked concrete temperature range II: 80		80°C/50°C				
Displacement	δ <sub>N0</sub> -factor	[mm/(N/mm²)]	0,02	0,03	0,03	0,04
	δ <sub>N∞</sub> -factor	[mm/(N/mm²)]	0,15	0,17	0,17	0,17

#### Table C4: Displacements under shear load

Threaded rod, HAS-U, HIT-V		M 8	M 10	M 12	M 16	
Displacement	$\delta_{V0}$ -factor	[mm/(kN)]	0,02	0,02	0,01	0,01
	δ <sub>V∞</sub> -factor	[mm/(kN)]	0,03	0,02	0,02	0,01

Injection system Hilti HIT-1 / HIT-1 CE	
Performances Displacements with threaded rod, HAS-U, HIT-V	Annex C 3